

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
21 February 2002 (21.02.2002)

PCT

(10) International Publication Number
WO 02/14589 A1

- (51) International Patent Classification⁷: **D03D 15/00** (74) Agent: **PELLEGATTA, Ottorino**; c/o Calvani, Salvi & Veronelli S.r.l., Piazza Duca d'Aosta, 4, I-20124 Milan (IT).
- (21) International Application Number: **PCT/IT01/00433**
- (22) International Filing Date: **6 August 2001 (06.08.2001)** (81) Designated States (*national*): **AU, US.**
- (25) Filing Language: **English** (84) Designated States (*regional*): **European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR).**
- (26) Publication Language: **English**
- (30) Priority Data:
MI2000U000483 11 August 2000 (11.08.2000) IT Published:
— with international search report
- (71) Applicant (*for all designated States except US*): **TECNO-TEXIL S.R.L. [IT/TT]; Via del Pianto, 11, I-24021 Albino (IT).** For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.
- (71) Applicant and
(72) Inventor: **MAZZER, Giacomo, Ezio [IT/TT]; Via XXIV Maggio 27, I-22036 Erba (IT).**



WO 02/14589 A1

(54) Title: **PROTECTIVE SHEATH FOR FLEXIBLE TUBES**

(57) Abstract: The protective sheath is made of a synthetic fabric having high tenacity unfinished weft and warp yarns. The count of the yarns used for making the synthetic fabric ranges from 400 to 2000 decitex and the number of yarns ranges from 62 to 70 yarns per centimetre, within a tolerance limit of ± 8 yarns per centimetre.

- 1 -

PROTECTIVE SHEATH FOR FLEXIBLE TUBES

TECHNICAL FIELD

The present invention relates to a protective sheath for covering flexible tubes that are customarily used in hydraulic systems of various kinds of equipment, machines and motor vehicles.

5

BACKGROUND ART

As known, the sheaths of the above mentioned kind are used mainly for the purpose of protecting the operatives and the environment in the case of a leakage or jet of oil caused by a failure or defective operation of the flexible tubes.

10

For attaining this purpose, the sheaths must assure in use an appropriate degree of safety and reliability in order to fulfil the requirements of the hydraulic systems of equipment, machines and motor vehicles which generally operate under very severe conditions as regards the mechanical and thermal stresses and are installed in places subject to the action of water, snow and dirt.

15

In particular, the sheaths must offer a good resistance to abrasion and flame and have to perform a sealing action in the case of leakage of pressurised oil from the flexible tube on which they are fitted.

20

Furthermore, the sheaths must contain the fluid stream issuing from the flexible tube in the case of an explosion thereof and they must assure an electrical resistivity similar to that of the tube on which they are fitted.

25

- 2 -

The conventional sheaths known in the art are adapted for use in operating conditions which mostly do not correspond to those of the user.

5 **DISCLOSURE OF THE INVENTION**

10 The object of the present invention is to provide a protective sheath improved as to its technical and manufactural features and adapted to assure in use a greater safety and reliability than that till now obtainable with the protective sheaths known in the art and available on the market, thereby meeting effectively the utilisation requirements in various operating conditions.

15 **BEST MODE FOR CARRYING OUT THE INVENTION**

20 According to the invention, the protective sheath is made of a synthetic fabric having high tenacity unfinished weft and warp yarns, the count of the yarns used for making the synthetic fabric ranging from 400 to 2000 decitex and the number of yarns ranging from 62 to 70 yarns per centimetre, within a tolerance limit of ± 8 yarns per centimetre.

25 According to a feature of the present invention, the yarns used to make the sheath are made of polyamide (PA) or polyester (PES).

30 According to another feature of the present invention, the protective sheath is made of two layers of synthetic fabric each having yarns of different colour in order to show the degree of weariness of the sheath and permit the replacement thereof.

35 In order to verify the degree of safety and reliability of the protective sheath of the invention, this has been subject to tests simulating the most frequent working conditions in which the flexible tubes may operate. In particular, the following tests have been carried out:

- 3 -

1. Abrasion Resistance Test
2. Pressure Test
3. Explosion Test
4. Flame Resistance Test
- 5 5. Resistivity Test
6. Pinhole Test

1. Abrasion Resistance Test

10 The abrasion resistance test has been carried out according to the specifications of the International Standard ISO 6945 (UNI En 7058). A specific equipment with an abrasion test sharp-edged instrument preloaded with 50 newtons has been used in this test.

The sheaths known in the art and available on the market have assured a resistance to abrasion up to 18000 cycles.

15 The sheath according to the invention has assured a resistance to abrasion up to 50000 cycles, with a maximum quantity of material removed equal to 20 milligrams.

20 At the end of the abrasion test, the single yarns of the fabric have been drawn out from the sheath with the object of subjecting them to a tensile test up to the ultimate tensile stress for the purpose of ascertaining the real structural deterioration due to the abrasion test. The tensile test showed that the fabric yarns of the sheath according to the invention after the abrasion resistance test were in a better condition than those of conventional sheaths and that they had an

25 ultimate tensile stress value which in the average was 300% greater.

2. Pressure Test

30 This test has been carried out for the purpose of verifying the ability of the sheath to withstand the pressure of oil by simulating the condition in which a jet of oil issues from the flexible tube because of a burst or failure thereof during operation. In the test, specimens of sheaths having a length of 330 mm

- 4 -

have been placed on a test bench with their ends fastened by means of clamps and subjected to increasing pressure values.

The conventional sheaths showed leakage at pressure values lower than 2 bars occurring few seconds after pressurisation.

- 5 The sheath according to the invention assured tightness up to a pressure value of 8 bars before starting to leak as the conventional sheaths. The leakage occurred 15 seconds after pressurisation.

3. Explosion Test

- 10 In order to carry out the explosion test, the sheaths have been fitted on a spirally wound flexible tube having an inner diameter of 19 mm according to the Standard 4SH-DIN 20023 and pressurised up to the minimum burst pressure value of 2.100 bars.

- 15 The sheaths of conventional kind were completely broken upon a burst at the middle of the tube whereby a great leakage of oil occurred.

The sheath according to the invention was only partially broken upon the burst at the middle of the tube and offered a better containment of the oil issuing from the tube.

20

4. Flame Resistance Test.

The flame resistance test has been carried out in accordance with the specifications of the International Standard ISO 8030 by exposing the sheaths to the flame for a period of 60 seconds.

- 25 During the exposure to flame, the conventional sheaths resisted for 8 seconds before completely melting and permitting the flame to propagate.

The sheaths according to the invention started to melt only after 15 seconds, offering at the same time a better barrier against propagation of flame.

30

5. Resistivity Test.

The resistivity test was performed following the specifications of the International Standard ISO 8031. The sheaths were fitted on various kinds of flexible tubes and the values of resistance per unit length were measured by applying to the flexible tubes covered by the sheath a d.c. voltage of 500 volts.

The sheath according to the invention showed a resistance per unit length of 3×10^6 to 5×10^6 ohms/meter, which is less than that required by the standard corresponding to 10^7 ohms/meter.

6. Pinhole Test

This test was performed by fitting the sheaths having a diameter of 30mm on a DIN 4SP tube with an inner diameter of 13 mm and an operating pressure of 420 bars. A pierce was formed in the tube with a diameter of 1mm for the purpose of simulating the so-called "pinhole effect". The tube was subjected to a test pressure of 210 bars in order to ascertain the operation of the sheaths.

By applying and keeping a pressure of 210 bars to the conventional sheaths, a continuous jet of oil was produced which issued from the sheaths in a very clearly way.

By applying and keeping a test pressure of 210 bars to the sheath according to the invention, a spot of oil appeared at the hole formed in the tube, but there was no leakage of oil through the sheath. The sheath of the invention offered therefore a better containment of oil.

From the foregoing it is clear that the sheath according to the invention reaches the aimed object. In particular, the protective sheath is improved as to the technical and manufactural features and is adapted to assure in operation a greater safety and reliability than that till now obtainable with the protective sheaths known in the art and available on the market. As a matter of fact the sheath of the invention is capable of containing any leakage (bleeding, dripping, jets caused by microporosity, bursts) which may occur in flexible

- 6 -

tubes of hydraulic systems of equipment, machines and motor vehicles of various kinds.

Furthermore, the sheath of the invention is made in compliance with National and International Standards relating safety and protection as to the components, their operation and reliability.

5

10

15

20

25

30

- 7 -

CLAIMS

- 5 1) A protective sheath characterised in that it is made of a synthetic fabric having high tenacity unfinished weft and warp yarns, the count of the yarns used for making the synthetic fabric ranging from 400 to 2000 decitex and the number of yarns ranging from 62 to 70 yarns per centimetre, within a tolerance limit of ± 8 yarns per centimetre.
- 10 2) A protective sheath according to claim 1, characterised in that the yarns used to make the sheath are made of polyamide (PA) or polyester (PES).
- 15 3) A protective sheath according to claim 1, characterised in that the yarns used to make the sheath are finished with a continuous dyeing process.
- 20 4) A protective sheath according to claim 1, characterised in that the yarns used to make the sheath are finished with a dyeing process and a calendering process.
- 25 5) A protective sheath according to claim 2, characterised in that the yarns of polyamide (PA) have a count equal to 470, 630, 940, 1400 or 1800 decitex.
- 30 6) A protective sheath according to claim 2, characterised in that the yarns of polyester (PES) have a count equal to 400, 500, 600, 800, 1000, 1100 or 2000 decitex.

- 8 -

7) A protective sheath according to claim 1, characterised in that it is made of two layers of synthetic fabric each having yarns of different colour in order to show the degree of weariness of the sheath and permit the replacement thereof.

5

10

15

20

25

30

INTERNATIONAL SEARCH REPORT

International Application No

PCT/IT 01/00433

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 D03D15/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 D03D F16L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DE 198 03 169 A (HUESKER) 29 July 1999 (1999-07-29) claims 1,3,6	1,2,6

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

22 November 2001

Date of mailing of the international search report

29/11/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Boutelegier, C

INTERNATIONAL SEARCH REPORT

Information on patent family members

Int: ☐ International Application No

PCT/IT 01/00433

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
DE 19803169 A	29-07-1999	DE 19803169 A1	29-07-1999



RECEIVED

JUL 2 - 2002

TC 1700